

Silvered Copper, rolled clad (Cu/Ag)

For more than 35 years we are producing rolled clad silvered copper. Due to decades of experience Schlenk has a high degree of expertise in the use and application of rolled clad tinned copper.

Typical Compositions of material:

Copper core: Cu-ETP (E-Cu58)
 Cu-HCP (SE-Cu58)
 Cu-OF

Silver layer: Ag99.99

Silver layer ratio: standard: 3% of total strip thickness
 available as single- or double sided

Strip thickness: 0.010 mm – 500 mm (0.0004" – 0.02")

Width: 0.6 mm – 330 mm (0.024" – 13.0")

Roll clad silvered copper foil is produced in coil.

Most dimensions are also available as sheet, cut to length, not levelled.

Narrow dimensions, mainly in widths below 8mm (0.32") are available mainly on traverse wound spools, or with limitations on pancake

Lot sizes:

We supply, quick and flexible, small lots for R&D as well as big lots.

Applications:

Solar; Automotive; Electronics, Medical Equipment, Decorative Purposes