

Cu-OF

Designation	EN / Cu-OF	EN / CW008A	UNS / C10200
-------------	------------	-------------	--------------

This very pure copper alloy is oxygen-free and finds its main use in brazing and in applications in high vacuum. This alloy is immune towards hydrogen embrittlement. It also does not contain elements that evaporate under high vacuum. Thin copper foil can be made with this material.

COMPOSITION OF MATERIAL

- Cu: $\geq 99,95\%$ • O: $\leq 0,001\%$

PHYSICAL PROPERTIES

· Density	8,93 g/cm ³
· Melting point	1083 °C
· Electrical conductivity	min. 58 m/Ω mm ² (at 20 °C R200)
· Electrical resistivity	max. 0,017241 Ω mm ² /m (at 20 °C R200)
· Temperature coefficient of electrical resistance	3,81·10 ⁻³ /K (at 0 to 150 °C R200)
· Thermal conductivity	394 W/K m (at 20 °C)
· Thermal capacity	0,386 J/g K (at 20 °C)
· Coefficient of thermal expansion (linear)	17,7·10 ⁻⁶ /K (at 20 to 300 °C)
· Modulus of elasticity (tensile)	110 GPa (at 20 °C R200)

MANUFACTURING PROGRAM	THICKNESS	WIDTH
Rolls, spools, sheets	0,006 - 0,4 mm	0,6 - 660 mm

*not all combinations of thickness and width are available
 or different dimensions please contact our technical service*

TEMPER ACCORDING TO DIN EN 13599			TYPICAL VALUES (information only)
	Tensile strength Rm in MPa	Yield strength Rp0,2 in MPa	Elongation in % L ₀ = 100 mm
R200	200 - 250	≤ 100	> 15
R220	220 - 260	≤ 140	> 15
R240	240 - 300	≥ 180	< 35
R290	290 - 360	≥ 250	< 20
R360	≥ 360	≥ 320	< 5

The values in the table are valid only for foils with thickness > 0,1 mm.

For further information please visit our website: <https://www.schlenk.com>
 You will find further information at: <https://copperalliance.eu>

Data in this publication is based on careful investigations and is intended for information only. All information shall not be binding, shall carry no warranty as to certain ingredients, as to the fitting for a special purpose, as to the merchantability, or as to the industrial property rights of third parties. Any and all users are obliged to carry out tests on their own authority as well as to check the suitability and the danger of the respective product for a particular application. SCHLENK assumes no liability in this regard; neither to the exactness nor to the completeness of the data. We apply our General Sales Conditions to be found on www.schlenk.com